

**EQUILEX CHEMICALS BV**

Jan van Galenstraat 54

3115 JG SCHIEDAM

The Netherlands

Tel : + 31 1 03 40 30 90

www.equilex.com

info@equilex.com

TYPICAL PROPERTIES

Ref.no: S SUNT
Rev.no: 01
Date: 29/08/2018
Origin: Taiwan

Suntack
Aromatic C9 hydrocarbon resins

PROPERTY	GA 100R	GA 120	GS 90	SK 120	SK 120B	YT 130	YT 140	U 90	U 101	U 120	U 120P	U 140
Softening point (°C)	100 ± 5	120 ± 5	100 ± 5	120 ± 5	120 ± 5	130 ± 5	140 ± 5	100 ± 5	110 ± 5	120 ± 5	120 ± 5	140 ± 5
Typical colour (G)	10	10	6	6	9	6	6	4	4	4	4	4
Bromine N°	< 30	< 30	< 30	< 30	< 30	< 30	< 30	< 25	< 25	< 25	< 25	< 25
Ash content	< 0.2 %	< 0.2 %	< 0.2 %	< 0.2 %	< 0.2 %	< 0.2 %	< 0.2 %	< 0.2 %	< 0.2 %	< 0.2 %	< 0.2 %	< 0.2 %

Test methods

Colour (Gardner) : ASTM D -1544 (50 % in Toluene)

Softening Point : ASTM-28-58

Bromine No : ASTM-1158

Ash content : ASTM D-482

Storage

Low to medium softening point resins in pellets may block, lump or fuse if stored during hot weather, upon prolonged storage or if stored near any heat source

Disclaimer of Liability

The information in this bulletin is believed to be accurate but all recommendations are made without warranty, since the conditions of use are beyond Equilex BV's control. Equilex BV disclaims any liability in connection with the use of the information which is illustrative only and does not warrant against infringement by reason of the use of any of its products in combination with other material or any process.